



Surface Technologies

Technical Process Bulletin

TURCO 1495

Polishing liquid for aluminium

Description

TURCO 1495 is a polishing liquid, typically used on aluminium and chromated surfaces.

Properties

TURCO 1495 is formulated based on mineral oil, waxes and polishing agents.

It can be applied manually or using a mechanical polishing device. Applied to aluminium this product will leave an invisible coating, protecting the substrate against oxidation.

When using **TURCO 1495** on painted aluminium first test on a small surface because of its abrasive properties.

Characteristics

Appearance:	viscous liquid
Density:	1,05 kg/L
Viscosity:	16 – 24 Poise
Storage:	5 – 30 °C
Shelf life:	1 year in closed packaging

Application

TURCO 1495 is applied without dilution by means of a cloth or polishing equipment.

Manual:

Put a small amount of **TURCO 1495** on a dry cloth and polish the substrate till oxidation or stains disappear. High gloss surfaces can be obtained by polishing afterwards the surface of the part with a dry cloth.

Mechanical:

Apply the product on a surface of maximum 1 m², using a polishing machine, and bring to bear low pressure. Move the machine to and fro to avoid the development of heat. High gloss surfaces can be obtained by polishing afterwards the surface of the part with a dry cloth.

Safety

Please read the detailed safety data sheet of the product.

N.V. Henkel Belgium S.A.

Havenlaan 16 Avenue du Port

B-1080 BRUSSEL - BRUXELLES

Tel : (+32) 2 421 25 55

Fax: (+32) 2 421 25 99

HRB 517 356 RCB

This information is based on our current level of knowledge. It is given in good faith but it is not intended to guarantee any particular properties. The users must satisfy themselves that there are no circumstances requiring additional information or precautions or the verification of details given herein.; This information is based on our current level of knowledge. It is given in good faith but it is not intended to guarantee any particular properties. The users must satisfy themselves that there are no circumstances requiring additional information or precautions or the verification of details given herein.

Revision date: 06/12/2004

Print date: 09/03/2005