



Surface Technologies

Technical Process Bulletin

P3-Scribex 342

ACID GRAFFITI REMOVER

Description

P3-Scribex 342 is a 'ready to use', acid, thixotropic product to remove graffiti from walls. This technology is typically used to remove epoxy layers.

Properties

P3-Scribex 342 is based on methylene chloride, but is free of phenol and chromates. This product thickens immediately after application as such making sure all active components stay in contact with the surface to be stripped.

P3-Scribex 342 is not recommended in combination with magnesium, high strength steel and natural stone. We advise to cover such components, before applying this product. For removing graffiti on natural stone and concrete, we recommend to use **P3-Scribex 341**.

It can be used on horizontal and vertical positioned walls and is compatible with bricks, construction steel and aluminium.

Characteristics

Appearance:	viscous, white-yellow liquid
Density:	1,26 kg / L (20°C)
Viscosity:	30 Poise
Storage:	5 – 30°C (out of sunlight)
Shelf life:	1 year in closed packaging

Application

P3-Scribex 342 can be applied without dilution by means of a brush, roller or non-misting spraying equipment.

Make sure adequate ventilation is available.

Leave the product on the surface to react with the paint layer(s) for a reasonable long time. Use a brush or cloth to improve its graffiti or paint removing properties.

To remove **P3-Scribex 342** we advise the following:

Make sure paint doesn't adhere to the surface anymore, using a brush, rag or a scraper.

Use high-pressure cold water cleaning to remove chemicals & remaining paint from the surface. Brushing while rinsing will lead to optimal results. Re apply, if necessary.

In case steel parts were stripped, apply a passivation to prevent corrosion.

Ideal working conditions are obtained between 20 – 25 °C (higher temperature brings shorter stripping time).

Safety

Please read the detailed safety data sheet of the product.

N.V. Henkel Belgium S.A.

Havenlaan 16 Avenue du Port

B-1080 BRUSSEL - BRUXELLES

Tel : (+32) 2 421 25 55

Fax: (+32) 2 421 25 99

HRB 517 356 RCB

This information is based on our current level of knowledge. It is given in good faith but it is not intended to guarantee any particular properties. The users must satisfy themselves that there are no circumstances requiring additional information or precautions or the verification of details given herein.; This information is based on our current level of knowledge. It is given in good faith but it is not intended to guarantee any particular properties. The users must satisfy themselves that there are no circumstances requiring additional information or precautions or the verification of details given herein.

Revision date: 06/12/2004

Print date: 09/03/2005